



THOR Tarp

DIV. OF **ODIN** INTERNATIONAL, INC



DuraShield 12,000 FR

Fire Retardant 4-ply
Woven Coated Polyethylene
Data Sheet

COUNT:	Nominal 16 x 16 tapes/inch	
WEIGHT:	9.25 oz per square yard (315 gsm)	
TENSILE STRENGTH: (Grab Method)	Warp - 320 lbs Weft - 320 lbs	ASTM D751 (Meth. A)
TEAR STRENGTH: (Tongue Method)	Warp - 50 lbs Weft - 50 lbs	ASTM D751 (Meth. B)
MULLEN BURST:	675 p.s.i.	ASTM D751
COATING THICKNESS:	2.0 mil average, both sides	
SCRIM TYPE:	Clear tapes, UV stabilized	
COLOUR:	Clear and colored coatings available	
ACCELERATED WEATHERING/U.V.:	More than 80% strength retention after 2000 hours	ASTM G53-84
(Q.U.V.[A-340 Lamps] 8 hrs U.V. @60° C/4 hrs condensation @50° C)		