



THOR Tarp

DIV. OF **ODIN** INTERNATIONAL, INC



ThoroShield 1850®

Vinyl Coated Polyester
"The Standard of the Industry"

Specifications:

<i>Property</i>	<i>Test Method</i>	<i>Value</i>
<i>Base Fabric</i>	<i>1000D x 1300D,</i>	<i>18 x 17 weave psi</i>
<i>Mill Roll Width</i>	<i>Standard Measure</i>	<i>61 1/4"</i>
<i>Weight</i>	<i>FS-191-5041</i>	<i>18 1/2 oz. / yd²</i>
<i>Grab Tensile Strength</i>	<i>FS-191-5100</i>	<i>410 lbs. x 410 lbs.</i>
<i>Strip Tensile Strength</i>	<i>FS-191-5102</i>	<i>300 lbs. x 300 lbs.</i>
<i>Tongue Tear Strength</i>	<i>FS-191-5134</i>	<i>100 lbs. x 100 lbs.</i>
<i>Adhesion</i>	<i>FS-191-5970</i>	<i>12 x 10 lbs. / inch</i>
<i>Abrasion Resistance</i>	<i>FS-191-5306</i>	<i>400 cycles</i>
<i>Hydrostatic Resistance</i>	<i>FS-191-5512</i>	<i>At least 600 lbs. psi.</i>
<i>Cold Crack</i>	<i>FS-191-5874</i>	<i>-40° F</i>
<i>U.V. Resistance</i>	<i>Weather-O-Meter</i>	<i>minimal fading 300 hrs</i>
<i>High Temp. Resistance</i>	<i>FS-191-5872</i>	<i>180° F (does not block)</i>

Visit our website at ThorTarp.com, email to info@ThorTarp.com or call us at 1-888-634-6462. Thousands of happy customers later, we are committed to your satisfaction!

ODIN International, Inc.

THOR Tarp & eTarp.com Divisions
PO Box 35, Curtis, MI 49820-0035
800-835-8467 888-634-6462 262-569-7171

CORPORATE HQ: P.O. BOX 811 • OCONOMOWOC, WI 53066-0811 • 262-569-7171 • FAX: 262-569-1511
TOLL FREE: 1-888-ODIN-INC • 1-888-634-6462 • EMAIL: INFO@THORTARP.COM

WWW.THORTARP.COM